

# Visual Quality Standard for Applied Window Film



## 1. SCOPE

Installed film on flat glass surfaces is not expected to have the same level of visual quality as glass.

The following criteria applies to the installed film only and not to any defect inherent in the glass.

2. Installed film has a discrete time for full adhesion to be effected since installation utilises a detergent solution in water to float the film onto the glass: the excess water is squeegeed out but inevitably residual water will remain between the film and glass. Often the time to achieve full adhesion is referred to as the adhesive cure time. Adhesion will be increasing from a lower value during this time. Visual and adhesive cure time is related to thickness of the film used. Typical visual cure times may be extended or shortened according to climatic conditions.

3. Inspection for optical quality can be made before full visual cure is attained. Table 1 provides a guide for typical visual cure times. It should be noted that effects during cure, such as water bubbles, water distortion, and water haze are not to be regarded as defects.

4. The glass with applied film shall be viewed at right angles to the glass from the room side, at a distance of not less than 2 metres. Viewing shall be done in natural daylight and not in direct sunlight, and shall assess the normal vision area with the exception of a 50mm wide band around the perimeter of the unit.

5. The installation shall be deemed acceptable if any of the following are unobtrusive, (effects during visual cure should be disregarded):

- Dirt Particles
- Water Haze
- Hair and Fibres
- Scores and Scratches
- Adhesive Gels
- Film Distortion
- Fingerprints
- Creases
- Insects
- Air Bubbles
- Edge Lift
- Nicks and Tears

Inspection may be made within 1 day of installation.

Obtrusiveness of blemishes shall be judged by looking through the film installation under lighting conditions described in 4.

6. The 50mm wide band around the perimeter shall be assessed in a similar process to that in 3 and 4, but a small number of particles is considered acceptable where the poor frame condition mitigates against the normally high quality standards aimed for.

7. Edge gaps will normally be 1-4mm. This allows for the water used in the installation to be squeegeed out. This ensures that film edges are not raised up by contact with the frame margin. Contact with the frame margin could lead to peeling of the film and is an installation fault.

For thicker safety films the edge gaps will normally be 1-4mm, with 1-5mm being acceptable for films of  $\geq 175\mu$ . Combination solar control safety films will also fall within this standard.

An edge gap of up to 2mm is recommended, especially for darker (tinted, metallised, tinted/metallised and sputtered) films, to minimise the light line around the edge of the installed film.

8. Splicing of films is necessary when larger panels of glass are treated. These glass panels are those where both

dimensions exceed the maximum width of film. The splice line itself should not be viewed as a defect. This line should be straight and should be parallel to one edge of the frame margin. The two pieces of film may be butt jointed and should be close but not touching; the maximum gap at any point in the splice line should be 1mm. Films of less than 50 $\mu$  may be overlapped, spliced or butt jointed.

9. It should be noted that visible light reflections can be changed by installation of window film. This is especially the case for films with deposited layers containing metal or metal alloys. This is not a defect but is a natural consequence of the high performance coatings used within the film.

10. Films for safety usage with respect of BS6262 Part 4 Safety shall be correctly marked in accordance with the relevant British Standard (BS6206).

Table 1

### TYPICAL CURE TIMES

Film Thickness/ $\mu$	Typical Cure Times/Days
up to 100	30
100 to 200	60
200 to 300	100
over 300*	140

\* but not exceeding 425 $\mu$ .

Whilst every attempt has been made to present up-to-date information, this data sheet, produced by the Glass and Glazing Federation, is issued for guidance but without responsibility for any advice given therein or omission therefrom or for the consequences of acting in reliance thereon and all liability on the part of the Glass and Glazing Federation however arising in connection therewith is hereby expressly disclaimed.

